


**NOTES:**

1. Application of stucco shall be in compliance with ASTM C926 and ASTM C1063 and the current Building Code.
2. Water-resistive Barrier - A minimum of two layers of Grade D paper or equivalent.
3. Lath - All lath and lath attachments shall be of corrosion-resistant materials. Lath shall be attached to framing members with attachments spaced not more than 7 inches on centers along supports.
4. Curing and interval - First and second coats of cement plaster shall be applied and moist cured for a minimum period of 48 hours.
5. Minimum interval between coats - The minimum interval between the first and second coats shall be 48 hours, and between the second coat and finish coat shall not be less than seven days.
6. Weep Screed - A minimum 0.019-inch (No. 26 galvanized sheet gage), corrosion-resistant weep screed, with a minimum vertical attachment flange of 3 1/2 inches shall be provided at or below the foundation plate line on exterior stud walls in accordance with ASTM C926. The weep screed shall be placed a minimum of 4 inches above the earth or 2 inches above paved areas.



STANDARD DRAWING

**CITY OF HOUSTON**  
HOUSTON PUBLIC WORKS  
BUILDING CODE ENFORCEMENT

**STUCCO DETAILS (WOOD FRAME)**

1002 WASHINGTON AVE., HOUSTON, TEXAS 77002

APPROVED BY:

BUILDING OFFICIAL

DATE:  
10-7-2024

DWG No:  
24-12-M

1 of 1