

NOTES:

- 1. Application of stucco shall be in compliance with ASTM C 926 and ASTM C 1063 and the provisions of Section 2510 of IBC.
- 2. Water-resistive Barrier A minimum of two layers of Grade D paper or equivalent. (Sec. 2510.6 IBC)
- 3. Lath All lath and lath attachments shall be of corrosion-resistant materials. Lath shall be attached to framing members with attachments spaced not more than 7 in. on centers along supports. (Sec. 7.10.2.1 ASTM C 1063)
- 4. Curing and interval First and second coats of cement plaster shall be applied and moist cured for a minimum period of 48 hours. (Sec. 2512.6 IBC)
- 5. Minimum interval between coats The minimum interval between the first and second coats shall be 48 hours, and between the second coat and finish coat shall not be less than seven days. (Table 2512.6 IBC)
- 6. Weep Screed A minimum 0.019-inch (No. 26 galvanized sheet gage), corrosion-resistant weep screed, with a minimum vertical attachment flange of $3\frac{1}{2}$ inches shall be provided at or below the foundation plate line on exterior stud walls in accordance with ASTM C 926. The weep screed shall be placed a minimum of 4 inches above the earth or 2 inches above paved areas. (Sec. 2512.1.2 IBC)



STANDARD DRAWING

CITY OF HOUSTON DEPARTMENT OF PUBLIC WORKS & ENGINEERING COMMERCIAL STUCCO DETAILS (WOOD FRAME)

1002 WASHINGTON AVE., HOUSTON, TEXAS 77002

APPROVED BY

DATE: 11 / 2 / 2016

DWG No: 16-04-C

1 of 1