



NOTES:

1. Installation of these materials shall be in compliance with ASTM C 926 and ASTM C 1063 and the provisions of the City of Houston Residential Code
2. Water-resistive Barrier - One layer of No. 15 asphalt felt, free from holes and breaks. It shall be applied horizontally, with the upper layer lapped over the lower layer not less than 2 inches. Where joints occur, felt shall be lapped not less than 6 inches. (R703.2)
3. Lath - All lath and lath attachments shall be of corrosion-resistant materials. Lath shall be attached to framing members with 1 1/2" long, 11 gage nails, or 7/8" long, 16 gage staples, spaced at no more than 6 inches. (R703.6.1)
4. Application - Each coat shall be kept in a moist condition for at least 48 hours prior to the application of the next coat. (R703.6.4)
5. Curing - The finish coat shall not be applied sooner than seven days after application of the second coat. (R703.6.5)
6. Weep Screenshot - A minimum No. 26 galvanized sheet gage, corrosion-resistant weep screenshot or plastic weep screenshot, with a minimum vertical attachment flange of 3 1/2 inches shall be provided at or below the foundation plate line. The weep screenshot shall be placed a minimum of 4 inches above the earth or 2 inches above paved areas. (R703.6.2.1)



STANDARD DRAWING
CITY OF HOUSTON
 HOUSTON PUBLIC
 WORKS

RESIDENTIAL NON FIRE-RATED
 STUCCO DETAILS (WOOD FRAME)
 1002 WASHINGTON AVE., HOUSTON, TEXAS 77002

APPROVED BY:
[Signature]
 BUILDING OFFICIAL
 DATE: 10/9/2018 DWG No: 18-13-R 1 of 1